



UL INTERNATIONAL (UK) LTD  
 Womersley House, Building C,  
 The Guildway,  
 Old Portsmouth Road,  
 Guildford. GU3 1LR.  
 United Kingdom.



designated according to Article 29 of the Regulation (EU) No 305/2011 and member of EOTA (European Organisation for Technical Assessment, [www.eota.eu](http://www.eota.eu))

## European Technical Assessment

**ETA 15/0415**  
**of 14/07/2015**

**Technical Assessment Body issuing the ETA and designated according to Article 29 of the Regulation (EU) No 305/2011: UL International (UK) Ltd**

**Trade name of the construction product**

Casco FireAcrylic

**Product family to which the construction product belongs**

Fire Stopping and Sealing Product:  
 • Linear Joint and Gap Seals

**Manufacturer**

Sika Sverige AB  
 163 08 Spånga  
 Sweden

**Manufacturing plant(s)**

A/003

**This European Technical Assessment contains**

9 pages including 1 Annex which forms an integral part of this assessment.

**This European Technical Assessment is issued in accordance with regulation (EU) No 305/2011, on the basis of**

ETAG 026-3, edition 2011, used as European Assessment Document (EAD).

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body. Any partial reproduction has to be identified as such.

## **Table of Contents**

|       |   |   |
|-------|---|---|
| I.    | SPECIFIC PARTS OF THE EUROPEAN TECHNICAL ASSESSMENT .....   | 3 |
| 1     | Technical description of the product.....   | 3 |
| 2     | Specification of the intended uses of the product in accordance with the applicable European Assessment Document (Hereinafter EAD): ETAG 026-3..... | 3 |
| 3     | Performance of the product and references to the methods used for its assessment.....   | 4 |
| 4     | ASSESSMENT AND VERIFICATION OF CONSTANCY OF PERFORMANCE (HEREINAFTER AVCP) SYSTEM APPLIED, WITH REFERENCE TO ITS LEGAL BASE .....                   | 5 |
| 5     | Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD .....                                  | 5 |
| 6     | Issued on: .....  | 6 |
|       | ANNEX A – Resistance to Fire Classification – Casco FireAcrylic .....   | 7 |
| A.1   | Flexible wall constructions according to 1.2.1 with wall thickness of minimum 100 mm .....  | 7 |
| A.1.1 | Linear joint seals, between head of flexible wall and soffit of concrete floor and vertical end of flexible wall and concrete wall.....             | 7 |
| A.2   | Rigid wall constructions according to 1.2.1 with wall thickness of minimum 150 mm .....   | 8 |
| A.2.1 | Linear joint or gap seal, between head of rigid wall and soffit of concrete floor / between rigid walls .....                                       | 8 |
| A.3   | Rigid floor constructions according to 1.2.1 with floor thickness of minimum 150 mm .....   | 9 |
| A.3.1 | Linear joint or gap seal, between floor slabs or between floor slab and wall with sealant to the top face of the floor only .....                   | 9 |

## I. SPECIFIC PARTS OF THE EUROPEAN TECHNICAL ASSESSMENT

### 1 Technical description of the product

- 1) Casco FireAcrylic is a sealant used to form linear gap seals where gaps are present in wall and floor constructions and linear joint seals where wall and floor constructions abut.
- 2) The Casco FireAcrylic is supplied in liquid form contained within 310 ml cartridges. The sealant is gunned into the aperture in the separating element/elements and around the service or services, to a specified depth utilising mineral fibre insulation backing material.
- 3) Casco FireAcrylic contains no carcinogenic substances or mutagenic substances, flame retardants or antimicrobiological agents.
- 4) The applicant has submitted a written declaration that Casco FireAcrylic does not contain substances which have to be classified as dangerous according to Directive 67/548/EEC and Regulation (EC) No 1272/2008 and listed in the "Indicative list on dangerous substances" of the EGDS - taking into account the installation conditions of the construction product and the release scenarios resulting from there.

In addition to the specific clauses relating to dangerous substances contained in this European technical Assessment, there may be other requirements applicable to the products falling within its scope (e.g. transposed European legislation and national laws, regulations and administrative provisions). In order to meet the provisions of the Construction Products Regulation, these requirements need also to be complied with, when and where they apply.

- 5) The use category of Casco FireAcrylic in relation to BWR 3 (Hygiene, health and environment) is IA1, S/W3

### 2 Specification of the intended uses of the product in accordance with the applicable European Assessment Document (Hereinafter EAD): ETAG 026-3

Detailed information and data is given in Annex A.

The intended use of system Casco FireAcrylic is to reinstate the fire resistance performance of gaps in and joints in and between flexible wall and rigid wall constructions, gaps in and joints between rigid floor constructions.

- 1) The specific elements of construction that the system Casco FireAcrylic may be used to provide a gap or joint seal in, are as follows:

Flexible walls: The wall must have a minimum thickness of 10 mm and comprise steel studs lined on both faces with minimum 2 layers of 12.5 mm thick boards.

Rigid walls: The wall must have a minimum thickness of 150 mm and comprise concrete, aerated concrete or masonry, with a minimum density of 650 kg/m<sup>3</sup>.

Rigid floors: The floor must have a minimum thickness of 150 mm and comprise aerated concrete or concrete with a minimum density of 650 kg/m<sup>3</sup>.

The supporting construction must be classified in accordance with EN 13501-2 for the required fire resistance period.

- 2) The system Casco FireAcrylic may be used to provide a linear joint or gap seal with specific supporting constructions and substrates (for details see Annex A).
- 3) The maximum permitted joint/gap width for system Casco FireAcrylic is 100 mm.

- 4) The maximum movement capability of system Casco FireAcrylic is  $\leq 7.5\%$
- 5) The provisions made in this European Technical Assessment are based on an assumed working life of the Casco FireAcrylic of 30 years, provided that the conditions laid down in sections 4.2/5.1/5.2 for the packaging/transport/ storage/installation/use/repair are met. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.
- 6) Type Z<sub>2</sub>: Intended for uses in internal conditions with humidity lower than 85 % RH excluding temperatures below 0°C, without exposure to rain or UV.

### 3 Performance of the product and references to the methods used for its assessment

| Product-type: Sealant                       |  | Intended use: Linear Joint & Gap Seal |
|---|--|---------------------------------------|
| Basic requirement for construction work     | Essential characteristic               | Performance                           |
|   | Mechanical resistance and stability    |                                       |
| -   | None                                   | Not relevant                          |
| Safety in case of fire                      |  |                                       |
| EN 13501-1                                  | Reaction to fire                       | Class D-s1, d1                        |
| EN 13501-2                                  | Resistance to fire                     | Annex A                               |
| Hygiene, health and environment             |  |                                       |
| EN 1026:2000                                | Air permeability (material property)   | No performance determined             |
| ETAG 026-3, Annex C                         | Water permeability (material property) | No performance determined             |
| Declaration of manufacturer                 | Release of dangerous substances        | Declaration of manufacturer           |
| Safety in use                               |  |                                       |
| EOTA TR 001:2003                            | Mechanical resistance and stability    | No performance determined             |
| EOTA TR 001:2003                            | Resistance to impact/movement          | No performance determined             |
| EOTA TR 001:2003<br>ISO 11600               | Adhesion                               | No performance determined             |
| Protection against noise                    |  |                                       |
| EN 10140-2/ EN ISO 717-1                    | Airborne sound insulation              | Rw(C;Ctr)= 62 (-1;-5) dB*             |
| EN 10140-3/ EN ISO 717-2                    | Impact sound insulation                | No performance determined             |
| Energy economy and heat retention           |  |                                       |
| EN 12664, EN 12667 or EN 12939              | Thermal properties                     | No performance determined             |
| EN ISO 12572<br>EN 12086                    | Water vapour permeability              | No performance determined             |
| General aspects relating to fitness for use |  |                                       |
| ISO 8339: 2005, ISO 9046: 2004 & ISO 7389   | Durability and serviceability          | Z <sub>2</sub>                        |

\* At 12 mm depth

**4 ASSESSMENT AND VERIFICATION OF CONSTANCY OF PERFORMANCE (HEREINAFTER AVCP) SYSTEM APPLIED, WITH REFERENCE TO ITS LEGAL BASE**

According to the decision 1999/454/EC – Commission Decision of date 22nd June 1999 on the procedure for attesting the conformity of construction products pursuant to Article 20(2) of Council Directive 89/106/EEC as regards fire stopping, fire sealing and fire protective products, published in the Official Journal of the European Union (OJEU) L178/52 of 14/07/1999, see <http://eur-lex.europa.eu/JOIndex.do> of the European Commission<sup>1</sup>, as amended, the system(s) of assessment and verification of constancy of performance (see Annex V to Regulation (EU) No 305/2011) given in the following table(s) applies (apply).

| Product(s)                              | Intended use(s)  | Level(s) or class(es) | System(s) |
|---|--|-----------------------|-----------|
| Fire stopping and Fire Sealing Products | For fire compartmentation and/or fire protection or fire performance | Any                   | 1         |

**5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD**

Tasks of the manufacturer:

Factory production control

The manufacturer shall exercise permanent internal control of production. All the elements, requirements and provisions adopted by the manufacturer shall be documented in a systematic manner in the form of written policies and procedures, including records of results performed. This production control system shall ensure that the product is in conformity with this European technical Assessment.

The manufacturer may only use initial / raw / constituent materials stated in the technical documentation of this European Technical Assessment.

The factory production control shall be in accordance with the Control Plan of 8<sup>th</sup> April 2013 relating to the European technical assessment ETA 15/0415 issued on 14/07/2015 which is part of the technical documentation of this European technical approval. The "Control Plan" is laid down in the context of the factory production control system operated by the manufacturer and deposited at UL International (UK) Ltd.

The results of factory production control shall be recorded and evaluated in accordance with the provisions of the Control Plan.

---

<sup>1</sup> Official Journal of the European Communities L178/52 of 14/7/1999

Other tasks of the manufacturer

Additional information

The manufacturer shall provide a technical data sheet and an installation instruction with the following minimum information:

(a) Technical data sheet:

- Field of application:
- Building elements for which the linear joint seal or penetration seal is suitable, type and properties of the building elements like minimum thickness, density, and - in case of lightweight constructions – the construction requirements.
- Limits in size, minimum thickness etc. of the joint or penetration seal
- Construction of the linear joint seal or penetration seal including the necessary components and additional products (e.g. backfilling material) with clear indication whether they are generic or specific.
- Services which the penetration seal is suitable, type and properties of the services like material, diameter, thickness etc. in case of pipes including insulation materials; necessary/allowed supports/fixings (e.g. cable trays)

(b) Installation instruction:

- Steps to be followed
- Procedure in case of retrofitting
- Stipulations on maintenance, repair and replacement

**6 Issued on:**

**14<sup>th</sup> July 2015**

Report by:



C. Johnson  
Staff Engineer  
Building and Life Safety Technologies

Reviewed by:




C. W. Miles  
Business Manager – Europe & Latin America  
Building and Life Safety Technologies

**For and on behalf of UL International (UK) Ltd.**

## ANNEX A – Resistance to Fire Classification – Casco FireAcrylic

### A.1 Flexible wall constructions according to 1.2.1 with wall thickness of minimum 100 mm

#### A.1.1 Linear joint seals, between head of flexible wall and soffit of concrete floor and vertical end of flexible wall and concrete wall



#### A.1.1.1


| Substrate               | Depth (mm) | Backing   | Classification                         |
|-------------------------|------------|---|--|
| Plasterboard / concrete | 12.5 min.  | 12.5 mm Stone wool 35 kg/m <sup>3</sup> plus 50 mm steel partition head track | <b>EI 120 – T – X – F – W 00 to 30</b> |
|                         |            | 20 mm Stone wool 35 kg/m <sup>3</sup> *                                       | <b>EI 120 – V – X – F – W 00 to 30</b> |
|                         | 25 min.    | 50 mm steel partition head track  | <b>EI 120 – T – X – F – W 00 to 30</b> |

\* Maximum partition/wall height of 3 metres

**A.2 Rigid wall constructions according to 1.2.1 with wall thickness of minimum 150 mm**

**A.2.1 Linear joint or gap seal, between head of rigid wall and soffit of concrete floor / between rigid walls**

**Joint Seal:** Casco FireAcrylic to either side (or any position between) or both sides of the wall, joint widths up to 30 mm



**A.2.1.1**

| Substrate            | Depth (mm)              | Backing                               | Classification   |
|----------------------|-------------------------|---------------------------------------|--|
| masonry/<br>concrete | 25 min.<br>(one side)   | 20 mm Stone wool 40 kg/m <sup>3</sup> | <b>E 240 – T – X – F – W 00 to 30</b><br><b>EI 60 – T – X – F – W 00 to 30</b>   |
|                      | 15 min.<br>(both sides) |                                       | <b>EI 240 – V – X – F – W 00 to 30</b><br><b>EI 240 – T – X – F – W 00 to 30</b> |
|                      | 25 min.<br>(one side)   | 48 mm Casco FireBacking               | <b>E 240 – T – X – F – W 00 to 30</b><br><b>EI 120 – T – X – F – W 00 to 30</b>  |




**A.3 Rigid floor constructions according to 1.2.1 with floor thickness of minimum 150 mm**

**A.3.1 Linear joint or gap seal, between floor slabs or between floor slab and wall with sealant to the top face of the floor only**

**Joint Seal:** Casco FireAcrylic to either side (or any position between) or both sides of the floor, joint widths up to 100 mm

Construction details:



**A.3.1.1**

| Substrate            | Depth (mm)                | Backing  | Classification   |
|----------------------|---------------------------|--|--|
| masonry/<br>concrete | 25 min.<br>(any position) | 25 mm Casco FireBacking                          | <b>E 120 – H – X – F – W 00 to 100</b><br><b>EI 60 – H – X – F – W 00 to 100</b> |
|                      | 25 min (top face)         |  | <b>EI 180 – H – X – F – W 00 to 100</b>  |
|                      | 15 min.<br>(both sides)   | 25 mm Stone wool 40 kg/m <sup>3</sup>            | <b>EI 120 – H – X – F – W 00 to 100</b>  |
|                      |                           | 25 mm Stone wool 140 kg/m <sup>3</sup>           | <b>EI 180 – H – X – F – W 00 to 100</b>  |
|                      | 15 min.<br>(both sides)   | 25 mm stone wool 35 kg/m <sup>3</sup> insulation | <b>EI 240 – T – X – F – W 00 to 30</b>   |