



Ersätter: 2010-08-25

Datum: 2014-11-21

Universal Flex Pistol 494331

Flexible polyurethane foam to be used in any kind of small breakthroughs in walls and other cavities..

For insulation and sealing between window- and door frames, fixation of wall panels and roof stones in house, car and boat.

Excellent noise and heat insulation values.

- **High permanent elasticity**
- **Long for about 20-25 linear meters when joint width of 30 mm**
-
- **Good adhesion to all common building material**

TECHNICAL DATA

Basis: One-component Polyurethane prepolymer

Propellant: Propane/Iso-butane/
Dimethylendifenyl-diisocyanate

Color: Off white to yellowish

Cell structure: Medium-fine, mainly closed structure.

Service temperature:

Short time: - 40°C to +100°C

Long term: - 40°C to + 80°C

Coverage: 23 running meters

Water absorption: 1,5 Vol.-%

Thermal conductivity: 0,04 W/mK

Tensile strength (DIN 53430): 5-6 N/cm²

Elongation at tension (DIN53430): 32%

Shear strength (DIN 53427): 3-4 N/cm²

Compression strength at 10 % stress DIN 53421:
1-2 N/cm²

Free of halogen compounds (Certificate No.885-1/2002 Eco institute, Köln).

APPLICATION DATA

Application temperature: +5°C to + 25°C (Optimum + 20°C). The can should have room temperature

Tool: Foam gun

Tack free time: Approx. 10 minutes at room temperature

Cutting time: Approx. 30 minutes when 30 mm width joint at room temperature. Longer time with thicker beads or lower temperature and humidity.

Curing time:

Max. 12 h at + 23°C

Max. 18 h at + 5°C

Stability load bearing: After approx. 12 hours (20 mm bread)

Storage life: 9 months, store in a cool dry well-ventilated area. STORE IN UPRIGHT POSITION. Keep container closed and sealed until ready for use.

PAINTABILITY

The cured foam can be over painted with most paints or sealed with an elastic sealant.

CHEMICAL RESISTANT

Good resistance to water, oil, gasoline, cleaning solvents and weak household chemicals.

LIMITATION

Cured foam is sensitive to UV-light and direct sunlight.

Never apply thicker layers than 25 mm, though cure will otherwise be difficult.

DIRECTIONS FOR USE

Use **gloves and eye protection and apron for your own security.**

Keep the can at room temperature. Too low temperature will give bad foaming and yield.

Higher temperature than +50°C will cause explosion of the can.

Secure good ventilation.

SURFACE PREPARATION

The joint interface must be clean and free from oils, loose aggregates, laitance, form release agents, waterproofing and other contaminants.

Secure window- and door frames carefully as the foam has an expansion force.

Priming is not required

The surface must be moistened well with water.

All construction components must be properly prepared prior to foam application. Chilled cans must be carefully warmed in water before usage. However, the can must not be heated over +50°C as there is a risk of bursting.

Cans which are too hot, for example after having been left in a vehicle during summer, must be cooled in water.

The can should be shaken occasionally during this process to obtain the required temperature faster.

Prior to work, and before the adapter is attached to the can, it must be shaken thoroughly at least 15-20 times.

Care must be taken that the can is not attached tilted into the thread or overturned. Once a can has been started, it should be used within two month time.

APPLICATION

The instructions, both for the can and the gun, must strictly be observed.

To extrude the foam, pressure has to be carefully applied to the gun trigger. Fresh foam spills must be removed immediately within the tack-free time with Casco Gun Cleaner 3937 or by mechanical means.

Moisture is needed for an even and rapid curing of the foam. Inadequate moistening or overfilling of joints and cavities may lead to an unwanted post-expansion of the foam. Once a can has been started, it should be used within four weeks. In order to achieve a fine and regular cell structure, please always attach an adapter tube on the applicator gun.

The fresh foam will expand by 1½ to 2 times. There for

care must be taken not to overfill joints. Please note that moisture is needed for an even and rapid curing of the foam.

Inadequate moistening or overfilling of joints and cavities may lead to an unwanted post-expansion of the foam.

Spray a small quantity of water on the joint surfaces. This will give better foaming and quicker cure.

Shake the container thoroughly (~20 times). Remove the protective cap. Connect the plastic nozzle to the can.

Hold the can upside down. Extrude the foam by pressing the trigger on the nozzle. This product can also be used with a gun.

The joint has to be filled to not more than approximately 40 %, as the foam expands during cure.

Spray a small amount of water on the foam when it has filled most of the joint. This will give a quicker cure. After curing, excessive foam can be cut away.

If there is a residue in the can, it can be used within a couple of weeks depending on storage temperature and humidity.

Be aware of that the product is extremely flammable, store an opened can in a well-ventilated place, definitely not in a fridge or freezer.

The nozzle should not be removed in this case. Cut off a few cm (enough to reach uncured foam) of the nozzle before using the can again

HANDLING AND CLEANING INSTRUCTIONS

Remove all excess foam adjacent to the joint and clean the equipment prior to cure with acetone.

Clean skin with water and soap or hand cleaner prior to curing.

Uncured product on equipment is cleaned with acetone or rapeseed oil. Cured product is removed mechanically.

Keep out of reach of children.

Do not empty into drains.

Our information is based on laboratory tests and practical experience and may, as such, be considered a guide in connection with choice of product and working method. As the user's working conditions are beyond our control, we do not assume any responsibility for the results. Our responsibility covers exclusively personal injury or damage to property which actually have been proved subsequent to faults and defects in one of the products manufactured by us.

Certifierad enligt:



Sika Sverige AB
163 08 Spånga, Sverige
Tel: +46 8 621 89 00
Web: www.casco.se



ENVIRONMENTAL ASPECTS

For additional health and safety information consult the Safety Data Sheet.

Our information is based on laboratory tests and practical experience and may, as such, be considered a guide in connection with choice of product and working method. As the user's working conditions are beyond our control, we do not assume any responsibility for the results. Our responsibility covers exclusively personal injury or damage to property which actually have been proved subsequent to faults and defects in one of the products manufactured by us.

Certifierad enligt:



Sika Sverige AB
163 08 Spånga, Sverige
Tel: +46 8 621 89 00
Web: www.casco.se
