

WETSTOP PC



WETSTOP PC is a pre-shaped, flexible inside corner cuff. WETSTOP PC is a polyethylene sealing cuff, laminated with a polypropylene non-woven on it's both sides. In combination with CASCO water membranes intended for sealing the penetrations in wall/wall/floor inside corner connections. Approved according ETAG 022 as a kit component in watertight covering kits of CASCO WETSTOP and CASCO AQUASTOP. For interior use.

- Approved according ETAG 022 as a kit component
- EC1 Plus: very low emission
- Crack bridging
- Watertight
- Waterproof
- Easy to apply
- Suitable on heated floor
- Good adhesion to CASCO water membranes

TECHNICAL DATA

Dimensions: 110 mm x 110 mm

Material thickness: ~ 0,35 mm

Colour: blue

Temperature resistance: -20°C to +90°C

Packaging: 20 pcs./carton

Storage: 24 months in cool, dry conditions, protect against sunlight

APPLICATIONS

WETSTOP PC in combination with CASCO water membranes is suitable:

- in private wet rooms: bathrooms and shower rooms
- in highly loaded public wet rooms: shower rooms in the sports facilities, hospitals, therapy rooms
- in laundry rooms
- in toilets
- on heated floor
- in interior areas

SUBSTRATE AND PREPARATION

normal absorbent substrates

- concrete
- cement screeds
- cement plaster
- lime-cement plaster
- gypsum boards

calcium sulphate substrates

- calcium sulphate screeds
- gypsum plaster

non-absorbent substrates

- ceramic coverings, stable, thoroughly cleaned and if necessary abraded

For priming instructions follow the relevant product data sheet of the water membrane to be used in combination.

REQUIREMENTS OF THE SUBSTRATES

The substrate should be sufficiently sound, loadable, solid and free of dust, dirt, oil, grease and interfering agents. Remove parting and sinter layers by appropriate measures. Old ceramic covering surfaces must be thoroughly cleaned and abraded if necessary. Gypsum plasters (according EN 13279-1) should have a residual moisture of $\leq 75\%$ RH. Cement-based screeds (28 days old): $\leq 85\%$ RH, cement-based screeds (heated): $\leq 75\%$ RH, calcium sulphate screeds must have residual moisture of $\leq 75\%$ RH, as floor heating screed $\leq 65\%$ RH. Heated screed temperature must be $\leq 20^\circ\text{C}$ during the WETSTOP KL installation phase and during the next 24 hours. Observe country-specific guidelines. Uneven substrates must be smoothed with the appropriate CASCO levelling compound as required.

RECOMMENDED METHOD OF WORKING

WETSTOP PC is used for sealing the penetrations in interior corner wall/wall/floor connections prior the membrane application in the entire area. WETSTOP PC sealing tape is embedded wrinkle free into the fresh CASCO water membrane and pressed directly to the substrate using a smoothing trowel or a spatula. For adhering WETSTOP PC use the same CASCO water membrane, which is supposed to be applied in the entire surface area (exception CASCO WETSTOP water membrane. For more information refer to the product data



sheet).

While connecting WETSTOP PC to different sealing accessories or foil membrane CASCO WETSTOP, ensure minimum 5 cm overlapping.

Water membrane in the entire surface could be applied directly after WETSTOP PC installation.

IMPORTANT

Pay attention to the product data sheet of the chosen CASCO water membrane. Follow the relevant product data sheet when using the complementary products.

DISPOSAL

Dispose of in accordance with the regulations. For disposal of product residues, washing water and containers with adherent product residues please, follow the local governmental regulations.

ENVIRONMENTAL APPROVALS

EMICODE EC1 PLUS

We guarantee that our products leave the factory in perfect condition. While our recommendations for use are based on tests and practical experience, they can only provide general guidance without any assurance as to product characteristics, since we have no influence over the conditions on site, the execution of the work or the method of processing. This product data sheet supersedes all previous editions.

Sika Sverige AB
163 08 Spånga, Sverige
Tel: +46 8 621 89 00
Web: www.casco.com